

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	135	150	165
Width	inches	52	55	***
Cutable width	inches	50	53	***
Fabric Yield	m/kg	4.15	4.80	5.61
Ounces/yards	Oz/sq.yd	4.0	4.4	4.9
Fiber content	100% POLYESTER			

Additional comments about technical specifications

Comments: Larger width is not considered to be out of specification.
Style may present distorted weft.

NCM

PFD	Off White/White	Dyed	Printed
5407.51.00	5407.51.00	5407.52.10	5407.54.00

DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - hang to dry %)	Warp (%)	Weft (%)
	6	5

Additional comments about dimensional stability

Comments: The shrinkage value is an average between the batches produced and may be subject to change.
Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.
Separate by light and dark colors.

WASHING INSTRUCTIONS



- hand wash




- do not bleach



- hang to dry



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Additional instructions to use with care symbols

- Do not wring.
- Do not use steam during ironing.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

Comments

- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluate (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- Claims will be accepted within 15 days after receipt of the goods.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager