

### TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	108	120	132
Width	inches	53	56	***
Cutable width	inches	51	54	***
Fabric Yield	m/kg	5.08	5.87	6.86
Ounces/yards	Oz/sq.yd	3.2	3.5	3.9
Fiber content	100% POLYESTER			

Additional comments about technical specifications  
Larger width is not considered to be out of specification.

### NCM

PFD	Off White/White	Dyed	Printed
5407.51.00	5407.51.00	5407.52.10	5407.54.00

### CUTTING INSTRUCTIONS

Required idle time	Type knife of court	Direction of court	Dimensional stability after rest
6	High-speed steel Ver	Required	---

Additional comments about cut  
When the mold parts are inserted inverted, occurs a difference in hue.

### DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - hang to dry %)	Warp (%)	Weft (%)
	5	5

Additional comments about dimensional stability  
We do not recommend machine drying.  
Do not leave dirty clothes together in a closed place for a long time,  
Always keep separated in a cool and ventilated place.  
Separate by light and dark colors. Use neutral soap. Do not twist.

### WASHING INSTRUCTIONS



- hand wash



- do not bleach



- hang to dry



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note: The symbols must appear in this order: washing, bleaching, drying, ironing and dry cleaning.

### Additional instructions to use with care symbols

- Do not tumble dry.
- Do not wring.
- Do not use steam during ironing.

### STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

### GENERAL COMMENTS

- Style may present distorted weft.
- Iron with protective fabric over the style to avoid seam marks of seams.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- Style have low resistance to washing, they should not be mixed with other colors and/ or fabric in the same piece.

Prepared by Sara Almeida: Quality / Kalimo  
Approved by Murilo Garcia: Technical Manager