

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	422	469	516
Width	inches	53	56	***
Cutable width	inches	51	54	***
Fabric Yield	m/kg	1.30	1.50	1.76
Ounces/yards	Oz/sq.yd	12.5	13.8	15.2
Fiber content	74% RAYON 11% POLYESTER 11% NYLON 4% SPANDEX			

Additional comments about technical specifications

Larger width is not considered to be out of specification.
REST TIME 48 HOURS.

NCM

Printed	Yarns of different colors
6006.44.00	6006.43.00

DIMENSIONAL STABILITY

Shrinkage after washing (Machine wash - dry flat %)	Length (%)	Width (%)
	10	8

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.
Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.
Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS



- maximum temperature for the machine wash 40C (105F) / delicate gentle



- do not bleach



- dry flat



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Additional instructions to use with care symbols

- Do not steam.
- Do not tumble dry.
- Do not wring.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluate (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager