

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	366	407	448
Width	inches	56	59	***
Cutable width	inches	54	57	***
Fabric Yield	m/kg	1.42	1.64	1.92
Ounces/yards	Oz/sq.yd	10.8	12.0	13.2
Fiber content	90% NYLON 4% POLYESTER 4% METALLIZED 2% SPANDEX			

Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 48 HOURS.

Style subject to light folding marks.

NCM

Yarns of different colors

6006.33.00

DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - hang to dry %)	Length (%)	Width (%)
	12	12

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

The style undergoes narrowing in the width after washing, resuming measurements after ironing.

WASHING INSTRUCTIONS



- hand wash




- do not bleach



- hang to dry



- maximum temperature for the iron heat 110C (230F)



- dryclean, any solvent, mild cycle

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Neon colors have low resistance to light and washing, they should not be mixed with other colors and / or fabric in the same piece, they should be washed separately.
- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- Remove the excess water without twisting, the style crumples easily.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- It is essential to inform the purchase order, the intention to mix light and dark colors in the same piece.
- It is recommended to perform solidity tests before cutting if you are going to mix light and dark colors in the same piece.

Prepared by Andreia: Quality / Kalimo
Approved by Murilo: Technical Manager