

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	113	125	138
Width	inches	47	50	***
Cutable width	inches	45	48	***
Fabric Yield	m/kg	5.45	6.30	7.37
Ounces/yards	Oz/sq.yd	3.3	3.7	4.1
Fiber content	97% COTTON 3% SPANDEX			

Additional comments about technical specifications

Larger width is not considered to be out of specification.

NCM

PFD	Off White/White	Dyed	Printed
5208.12.00	5208.22.00	5208.32.00	5208.52.00

DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - dry flat %)	Warp (%)	Weft (%)
	10	8

Additional comments about dimensional stability

We do not recommend machine drying.

Do not leave dirty clothes together in a closed place for a long time,

Always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS



- hand wash




- do not bleach



- dry flat



- maximum temperature for
the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.
- Remove the excess water without twisting; the style crumples easily.
- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.

Prepared by Andreia: Quality / Kalimo
Approved by Murilo: Technical Manager