

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	36	40	44
Width	inches	49	52	***
Cutable width	inches	47	50	***
Fabric Yield	m/kg	16.40	18.94	22.15
Ounces/yards	Oz/sq.yd	1.1	1.2	1.3
Fiber content	75% COTTON 25% SILK			

Additional comments about technical specifications

Larger width is not considered to be out of specification.

NCM

PFD	Off White/White	Dyed	Printed
5212.11.00	5212.12.00	5212.13.00	5212.15.00

DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - dry flat %)	Warp (%)	Weft (%)
	8	5

Additional comments about dimensional stability

We do not recommend machine drying.

Do not leave dirty clothes together in a closed place for a long time,

Always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS




- hand wash



- do not bleach



- dry flat



- maximum temperature for
the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Additional instructions to use with care symbols

- Do not tumble dry.
- Do not wring.
- Do not use steam during ironing.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Neon colors have low resistance to light and washing, they should not be mixed with other colors and / or fabric in the same piece, they should be washed separately.
- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- Remove the excess water without twisting, the style crumples easily.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- It is essential to inform the purchase order, the intention to mix light and dark colors in the same piece.
- It is recommended to perform solidity tests before cutting if you are going to mix light and dark colors in the same piece.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager